

Woodtype **SMOKED OAK** heart-smoked

Description 3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The sorting Auslese is essentially knot-free*, with a lively structure.

Brinell hardness 4,2 kp
Gross density 0,71 g | cm³

1-Strip Country House Flooring SMOKED OAK Auslese "Mailand"



Surfaces


- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Auslese
Healthy knots	fill ø 8 mm allowed
Black knots	fill ø 8 mm allowed
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	scattered allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	light mirror alongside allowed

Technical data					
Thickness:	15 mm Useful layer: approx. 5 mm				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="1" style="width: 100%;"> <tr> <td style="width: 50%;">m² pkg. 2,28</td> <td style="width: 50%;">m² pal. 111,72</td> </tr> <tr> <td>kg pkg. 23</td> <td>kg pal. 1127</td> </tr> </table>		m² pkg. 2,28	m² pal. 111,72	kg pkg. 23	kg pal. 1127
m² pkg. 2,28	m² pal. 111,72				
kg pkg. 23	kg pal. 1127				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					




Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

1-Strip Country House Flooring SMOKED OAK Design "Zürich"



Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Also available as

- System board
(Fixed length 1100 mm)
- Kreativ 10,7 mm



*on special order only, with limited demands

Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data	
Thickness:	15 mm Useful layer: approx. 5 mm
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m ² pkg.	2,28
m ² pal.	111,72
kg pkg.	23
kg pal.	1127
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>	



Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. Special features are the streaky colour differences (light dark). The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

1-Strip Country House Flooring SMOKED OAK Design "Genf"



streaky

Surfaces


- Oil | wax oxidative dried
- Untreated sanded



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data	
Thickness:	15 mm Useful layer: approx. 5 mm
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m ² pkg.	2,28
m ² pal.	111,72
kg pkg.	23
kg pal.	1127
<input checked="" type="checkbox"/>	Floating laying
<input checked="" type="checkbox"/>	Glued laying
<input checked="" type="checkbox"/>	Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>




Woodtype **SMOKED OAK** heart-smoked

Description 3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The special feature is the white pore. The sorting Design is slightly to very knotty with a lively structure.


Brinell hardness 4,2 kp
Gross density 0,71 g | cm³

1-Strip Country House Flooring SMOKED OAK Design "Zermatt"



Surfaces

- Oil | wax oxidative dried
- Brushed
- Pore white



NOVELTIES

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	scattered allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data					
Thickness:	15 mm Useful layer: approx. 5 mm				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m² pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m² pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg pal. 1127</td> </tr> </table>		m² pkg. 2,28	m² pal. 111,72	kg pkg. 23	kg pal. 1127
m² pkg. 2,28	m² pal. 111,72				
kg pkg. 23	kg pal. 1127				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					

Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. Special features are the distinctive alongside and crosswise mirrors. The sorting Ambiente is slightly to very knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

1-Strip Country House Flooring SMOKED OAK Ambiente "Turin"



Surfaces


Oil | WAX oxidative dried



Symbol picture - may vary in colour and structure

Sorting guidelines	Ambiente
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	scattered allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	allowed (medium to high)

Technical data	
Thickness:	15 mm Useful layer: approx. 5 mm
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m² pkg. 2,28	m² pal. 111,72
kg pkg. 23	kg pal. 1127
<input checked="" type="checkbox"/> Floating laying	
<input checked="" type="checkbox"/> Glued laying	
<input checked="" type="checkbox"/> Suitable for underfloor heating	
<small>when gluing the entire area with solvent-free adhesives</small>	



Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. Special features are the naturally occurring colour differences (light dark). The sorting Ambiente is slightly to very knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

1-Strip Country House Flooring SMOKED OAK Ambiente "Luzern" Kreativ



Surfaces


- Oil | wax oxidative dried
- Untreated sanded



Symbol picture - may vary in colour and structure

Sorting guidelines	Ambiente
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data					
Thickness:	10,7 mm Useful layer: approx. 3 mm				
Width:	150 mm				
Length:	Lengthsystem 7 layers 1900 mm (11 layers pkg.) 4 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="1" style="width: 100%;"> <tr> <td>m² pkg. 3,04</td> <td>m² pal. 106,40</td> </tr> <tr> <td>kg pkg. 21,20</td> <td>kg pal. 745</td> </tr> </table>		m ² pkg. 3,04	m ² pal. 106,40	kg pkg. 21,20	kg pal. 745
m ² pkg. 3,04	m ² pal. 106,40				
kg pkg. 21,20	kg pal. 745				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					




Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

1-Strip Plank Flooring SMOKED OAK "Herringbone"



Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour




*on special order only, with limited demands

Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and across allowed

Technical data	
Thickness:	15 mm Useful layer: approx. 5 mm
Width:	150 mm
Length:	Fixed length 475* mm or 950** mm (8 layers pkg)
Connection:	Tongue and groove <small>One layer 475 mm consists of 2 boards* One layer 950 mm consists of 1 boards**</small>
m ² pkg.	1,10
m ² pal.	53,90
kg pkg.	10,7
kg pal.	527
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>	



Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The sorting Trend-Epoca is knotty, with a lively structure.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

2-Strip Plank Flooring SMOKED OAK "Trend-Epoca"



Surfaces


- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Trend-Epoca
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data					
Thickness:	15 mm Useful layer: approx. 5 mm				
Width:	140 mm				
Length:	Fixed length 2400 mm (8 layers pkg.)				
Connection:	Tongue and groove				
<table border="1" style="width: 100%;"> <tr> <td>m² pkg. 2,69</td> <td>m² pal. 112,98</td> </tr> <tr> <td>kg pkg. 26,2</td> <td>kg pal. 1104</td> </tr> </table>		m ² pkg. 2,69	m ² pal. 112,98	kg pkg. 26,2	kg pal. 1104
m ² pkg. 2,69	m ² pal. 112,98				
kg pkg. 26,2	kg pal. 1104				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives					



Woodtype	SMOKED OAK heart-smoked
Description	3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. The special features are the naturally occurring colour differences (light dark). The sorting Trend-Epoca is knotty, with a lively structure. Partially with sapwood.
Brinell hardness	4,2 kp
Gross density	0,71 g cm ³

2-Strip Plank Flooring SMOKED OAK "Trend-Colour"



Surfaces

- Oil | wax oxidative dried



Symbol picture - may vary in colour and structure

Sorting guidelines	Trend-Colour
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	allowed (partly filled)
Curled spots differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

Technical data					
Thickness:	15 mm Useful layer: approx. 5 mm				
Width:	140 mm				
Length:	Fixed length 2400 mm (8 layers pkg.)				
Connection:	Tongue and groove				
<table border="1" style="width: 100%;"> <tr> <td>m² pkg. 2,69</td> <td>m² pal. 112,98</td> </tr> <tr> <td>kg pkg. 26,2</td> <td>kg pal. 1104</td> </tr> </table>		m ² pkg. 2,69	m ² pal. 112,98	kg pkg. 26,2	kg pal. 1104
m ² pkg. 2,69	m ² pal. 112,98				
kg pkg. 26,2	kg pal. 1104				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives					

