BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype BEECH steamed

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander wa-

ter, the Beech without heartwood receives a light, slightly reddish to deep reddish

brown colour. The sorting Klassiker is essentially knot-free*, with a simple structure.

Brinell hardness 4,0 kp Gross density 0,72 g | cm³

2-Strip Plank Flooring BEECH steamed "Klassiker"



SURFACES

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel



www.bergland-parkett.at

Sorting guidelines		
Healthy knots	to approx. 5 mm allowed (partly filled)	
Black knots	to approx. 5 mm allowed (partly filled)	
Healthy red heart	not allowed	
Healthy black heart	not allowed	
Cracks	not allowed	
Curled Spots differences in structure	not allowed	
Natural colour differences	slightly allowed	
Natural fiber orientation	partly allowed	
Wormholes and insect-ate-spots	not allowed	
Sapwood	not allowed	
Red or brown spots	not allowed	
Stains from storage and light blueness	not allowed	
Knocked spots	not allowed	
Mirror	slightly allowed	

_		
	hnica	l data
15.	1 11 11(. (.	

Length

Thickness 15 mm Useful layer approx. 5 mm

8 layers 2400 mm

Width 140 mm

Fixlength
(8 layers | pkg)

Connection Tongue and groove

m²|pkg. 2,69 | m²|pal. 112,98

kg|pkg. 26,2 | kg|pal. 1104

▼ Floating laying

Glued laying

✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

