BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	BEECH	steamed
		310011100

Description 3 layers of hardwood. Due to the steaming with vitalized Grander water, the Bee-

ch receives a light, slightly reddish to deep reddish brown colour. The sorting Wohn-

gefühl is knotty, with a medium structure.

Brinell hardness 4,0 kp The creative program consists of 3 layers hardwood, where the Gross density 0,72 g | cm³ middle layer and the under layer can vary to the top layer.

## 1-Strip Country House Flooring BEECH steamed Wohngefühl Kreativ "Bregenz"



## **SURFACES**

- Oil | wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



www.bergland-parkett.at

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	to approx. 35 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	slightly allowed (partly filled)
Curled Spots   differences in structure	slightly allowed
Natural colour differences	allowed
Natural fiber orientation	to one-third allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	slightly allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	allowed

-				
	hr		ıl data	4
15.		11( . ( )		

Thickness 10,7 mm Useful layer approx. 3 mm

Width 150 mm

Length Lengthsystem 7 layers 1900 mm

(11 layers | pkg) 4 layers 950\* mm

Connection Tongue and groove

One layer 950\* mm consists of 2 boards

 $m^2 | pkg. 3,14$  |  $m^2 | pal. 109,90$ 

kg|pkg. 23 | kg|pal. 805

✓ Glued laying. Prescribed according to the EU standard. Floating installation is technically possible

Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

