

Woodtype **SMOKED OAK** european heart-smoked

Description 3 layers of the same hardwood. The European Oak receives a blackish-brown colour due to a special fumigation procedure. Special features are the streaky colour differences (light | dark). The sorting Design is slightly to very knotty, with a lively structure.

Brinell hardness 4,2 kp
 Gross density 0,71 g | cm³

1-Strip Country House Flooring **SMOKED OAK** european Design „Genf“



SURFACES

- Oil | wax oxidative dried
- Varnished 7-times



www.berglund-parkett.at

Symbol picture - may vary in colour and structure

| Sorting guidelines | |
|--|---|
| Healthy knots | allowed (partly filled) |
| Black knots | allowed (partly filled) |
| Healthy red heart | not allowed |
| Healthy black heart | not allowed |
| Cracks | allowed (partly filled) |
| Curlted Spots differences in structure | allowed |
| Natural colour differences | allowed |
| Natural fiber orientation | allowed |
| Wormholes and insect-ate-spots | not allowed <small>are allowed in middle layer and back layer**</small> |
| Sapwood | partly allowed |
| Red or brown spots | allowed |
| Stains from storage and light blueness | allowed |
| Knocked spots | not allowed |
| Mirror | alongside and crosswise allowed |

| | | |
|---|----------------------------------|--|
| Thickness | 15 mm | Useful layer approx. 5 mm |
| Width | 150 mm | |
| Length | Lengthsystem (8 layers pkg) | 5 layers 1900 mm 3 layers 950* mm |
| Connection | Tongue and groove | <small>Due to the technical drying, there are no longer any pests, only the holes in the middle layer and back layer**</small> |
| <small>One layer 950* mm consists of 2 boards</small> | | |
| m ² pkg. 2,28 | | m ² pal. 111,72 |
| kg pkg. 23 | | kg pal. 1127 |
| <input checked="" type="checkbox"/> Floating laying | | |
| <input checked="" type="checkbox"/> Glued laying | | |
| <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small> | | |

