BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	PEAR	steamed
----------	------	---------

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander wa-

ter, the Pear without heartwood receives a warm, reddish brown colour. The sorting

Wohngefühl is knotty, with a medium structure.

Brinell hardness 4,5 kp Gross density 0,72 g | cm³

1-Strip Country House Flooring PEAR steamed Wohngefühl Systemboard "Madrid"





SURFACES

- Oil | wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



www.bergland-parkett.at

Sorting guidelines			
Healthy knots	allowed (partly filled)		
Black knots	to approx. 35 mm allowed (partly filled)		
Healthy red heart	not allowed		
Healthy black heart	not allowed		
Cracks	slightly allowed (partly filled)		
Curled Spots differences in structure	slightly allowed		
Natural colour differences	allowed		
Natural fiber orientation	to one-third allowed		
Wormholes and insect-ate-spots	not allowed		
Sapwood	not allowed		
Red or brown spots	slightly allowed		
Stains from storage and light blueness	not allowed		
Knocked spots	not allowed		
Mirror	not allowed		

Technical data

Thickness 15 mm Useful layer approx. 5 mm

Width 150 mm

Length Fixlength 8 layers 1100 mm

(8 layers | pkg)

Connection Tongue and groove

m² | pkg. 1,32 | m² | pal. 64,68

kg|pkg. 12 kg|pal. 588

▼ Floating laying

Glued laying

✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

