TYPES OF WOOD ALDER natural|steamed - ASH - BEECH natural|steamed - BIRCH

BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	BLACK WALNUT steamed
Description	3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Black Walnut receives a light brown to intensive dark brown colour. A special feature is the proportion of sapwood. The Ambiente grade is slightly to very knotty with a lively structure.
Brinell hardness Gross density	3,4 kp 0.64 a l cm³

1-Strip Country House Flooring BLACK WALNUT steamed Ambiente "Stams"

SURFACES

- Oil | WAX oxidative dried
- Varnished 7-times
- ✓ Untreated sanded

also available as

Systemboard (Fixlength 950 mm) Width 145 mm

www.bergland-parkett.at			
Sorting guidelines			
Healthy knots	allowed (partly filled)		
Black knots	allowed (partly filled)		
Healthy red heart	not allowed		
Healthy black heart	not allowed		
Cracks	allowed (partly filled)		
Curled Spots differences in structure	allowed		
Natural colour differences	allowed		
Natural fiber orientation	allowed		
Wormholes and insect-ate-spots	not allowed		
Sapwood	allowed		
Red or brown spots	allowed		
Stains from storage and light blueness	allowed		
Knocked spots	not allowed		
Mirror	not allowed		



Technical data

Thickness	15 mm	Useful layer approx. 5 mm		
Width	150 mm			
Length	Lengthsystem	5 layers 1900 mm		
	(8 layers pkg)	3 layers 950* mm		
	Systemboard	8 layers 950 mm		
Connection Tongue and groove				
One layer 950* mm consists of 2 boards				
m² pkg.	2,28 1,10**	m² pal. 111,72 53,90**		
kg pkg.	23 11**	kg pal. 1127 539**		
Floating laying				
✓ Glued laying				
Suitable for underfloor heating when gluing the entire area with solvent-free adhesives				

