

Woodtype

# ALDER steamed

**Description** 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Alder without heartwood receives a light brown, reddish colour with decent brown colour inclusions. The sorting Wohngefühl is knotty, with a medium structure.

Brinell hardness 1,7 kp  
Gross density 0,49 g | cm³

## 1-Strip Country House Flooring ALDER steamed Wohngefühl „Kufstein“



### SURFACES

- ☒ Oil | wax oxidative dried
- ☒ Varnished 7-times
- ☒ Untreated sanded
- ☒ Bevel
- ☒ Special colour



[www.bergland-parkett.at](http://www.bergland-parkett.at)

Symbol picture - may vary in colour and structure

### Sorting guidelines

Healthy knots	allowed (partly filled)
Black knots	to approx. 35 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	slightly allowed (partly filled)
Curled Spots   differences in structure	slightly allowed
Natural colour differences	allowed
Natural fiber orientation	to one-third allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	slightly allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

### Technical data

Thickness	15 mm	Useful layer approx. 5 mm
Width	150 mm	
Length	Lengthsystem	6 layers 1900 mm
	(8 layers   pkg)	2 layers 950* mm

Connection Tongue and groove

One layer 950\* mm consists of 2 boards

m² | pkg. 2,28

m² | pal. 111,72

kg | pkg. 23

kg | pal. 1127

☒ Floating laying

☒ Glued laying

☒ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives



