BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype BEECH natural

Description 3 layers of the same hardwood. The natural Beech has a pleasant, naturally light to

brownish colour. The sorting Design is slightly to very knotty, with a lively structure.

Brinell hardness 4,0 kp Gross density 0,72 g | cm³

## 1-Strip Country House Flooring BEECH natural Design "Wels"



- Oil | wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



www.bergland-parkett.at

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy black heart	allowed
Cracks	allowed (partly filled)
Curled Spots   differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	allowed

-		 	
Tec	hn		ata
15.			

Thickness 15 mm Useful layer approx. 5 mm

Width 150 mm

Length Lengthsystem 6 layers 1900 mm

(8 layers | pkg) 2 layers 950\* mm

Connection Tongue and groove

One layer 950\* mm consists of 2 boards

m<sup>2</sup> | pkg. 2,28 | m<sup>2</sup> | pal. 111,72

kg|pkg. 23 | kg|pal. 1127

✓ Floating laying

Glued laying

✓ NOT suitable for underfloor heating when gluing the entire area with solvent-free adhesives

