

Woodtype

BIRCH

Description 3 layers of the same hardwood. The Birch without heartwood has a light, wheaten colour with distinctive colour inclusions. The sorting Wohngefühl is knotty, with a medium structure.

Brinell hardness 2,8 kp

Gross density 0,65 g | cm³

1-Strip Country House Flooring BIRCH Wohngefühl „Innsbruck“



SURFACES

- ☒ Oil | wax oxidative dried
- ☒ Varnished 7-times
- ☒ Untreated sanded



www.bergland-parkett.at

Symbol picture - may vary in colour and structure

Sorting guidelines

| | |
|---|--|
| Healthy knots | allowed (partly filled) |
| Black knots | to approx. 35 mm allowed (partly filled) |
| Healthy red heart | not allowed |
| Healthy black heart | not allowed |
| Cracks | slightly allowed (partly filled) |
| Curled Spots differences in structure | slightly allowed |
| Natural colour differences | allowed |
| Natural fiber orientation | to one-third allowed |
| Wormholes and insect-ate-spots | not allowed |
| Sapwood | not allowed |
| Red or brown spots | slightly allowed |
| Stains from storage and light blueness | not allowed |
| Knocked spots | not allowed |
| Mirror | not allowed |

Technical data

| | | |
|-----------|------------------|---------------------------|
| Thickness | 15 mm | Useful layer approx. 5 mm |
| Width | 150 mm | |
| Length | Lengthsystem | 6 layers 1900 mm |
| | (8 layers pkg) | 2 layers 950* mm |

Connection Tongue and groove

One layer 950* mm consists of 2 boards

m² | pkg. 2,28

m² | pal. 111,72

kg | pkg. 23


kg | pal. 1127

☒ Floating laying

☒ Glued laying

☒ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure