BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



SMOKED OAK european heart-smoked

Description 3 layers of the same hardwood. The European Oak receives a blackish-brown

colour due to a special fumigation procedure. Special features are the distinctive alongside and crosswise mirrors. The sorting Ambiente is slightly to very knotty, with a

lively structure.

Brinell hardness 4,2 kp Gross density 0,71 g | cm³

## 1-Strip Country House Flooring SMOKED OAK european Ambiente "Turin"



## **SURFACES**

Oil | wax oxidative dried



www.bergland-parkett.at

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	allowed (partly filled)
Curled Spots   differences in structure	slightly allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed are allowed in middle layer and back layer**
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

-				
	っわり	100	I da	t 🔿
15.		110.01	1 (1(1	1 ( )

Thickness 15 mm Useful layer approx. 5 mm

Width 150 mm

Length Lengthsystem 6 layers 1900 mm (8 layers | pkg) 2 layers 950\* mm

Connection Tongue and groove Due to the technical drying, there are no longer any pests, only the holes in the middle layer and back layer 950\* mm consists of 2 boards layer\*\*

m²|pkg. 2,28 | m²|pal. 111,72

kg|pkg. 23 kg|pal. 1127

✓ Floating laying

Glued laying

✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

