

Woodtype

OAK european

Description 3 layers of the same hardwood. The European Oak has a middle brown to reddish brown colour. Special features are the natural colour differences (light | dark). The sorting Ambiente is mottled, slightly to very knotty, with a lively structure.

Brinell hardness 4,2 kp
 Gross density 0,71 g | cm³

1-Strip Country House Flooring OAK european Ambiente „Sölden“



brushed, white

SURFACES

- ☒ Oil | wax oxidative dried
- ☒ Varnished 7-times
- ☒ Untreated sanded
- ☒ Brushed
- ☒ Bevel
- ☒ Special colour



Symbol picture - may vary in colour and structure

www.bergland-parkett.at

Sorting guidelines

| | |
|--|---|
| Healthy knots | allowed (partly filled) |
| Black knots | allowed (partly filled) |
| Healthy red heart | not allowed |
| Healthy black heart | not allowed |
| Cracks | not allowed |
| Curlled Spots differences in structure | allowed |
| Natural colour differences | allowed |
| Natural fiber orientation | allowed |
| Wormholes and insect-ate-spots | not allowed <small>are allowed in middle layer and back layer**</small> |
| Sapwood | partly allowed |
| Red or brown spots | allowed |
| Stains from storage and light blueness | allowed |
| Knocked spots | not allowed |
| Mirror | alongside and crosswise allowed |

Technical data

| | | |
|-----------|------------------|---------------------------|
| Thickness | 15 mm | Useful layer approx. 5 mm |
| Width | 150 mm | |
| Length | Lengthsystem | 6 layers 1900 mm |
| | (8 layers pkg) | 2 layers 950* mm |

Connection Tongue and groove Due to the technical drying, there are no longer any pests, only the holes in the middle layer and back layer**

One layer 950* mm consists of 2 boards

m² | pkg. 2,28

m² | pal. 111,72

kg | pkg. 23

kg | pal. 1127

☒ Floating laying

☒ Glued laying

☒ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives

