

Woodtype

## PEAR steamed

**Description** 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Pear without heartwood receives a warm, reddish brown colour. The sorting Trend-Epoca is knotty, with a lively structure.

Brinell hardness 4,5 kp  
Gross density 0,72 g | cm³

## 2-Strip Plank Flooring PEAR steamed „Trend-Epoca“



### SURFACES

- ☒ Oil | wax oxidative dried
- ☒ Varnished 7-times
- ☒ Untreated sanded
- ☒ Special colour



[www.bergland-parkett.at](http://www.bergland-parkett.at)

Symbol picture - may vary in colour and structure

### Sorting guidelines

Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	allowed (partly filled)
Curled Spots   differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

### Technical data

Thickness	15 mm	Useful layer approx. 5 mm
Width	140 mm	
Length	Fixlength	8 layers 2400 mm
	(8 layers   pkg)	

Connection Tongue and groove

m² | pkg. 2,69

m² | pal. 112,98

kg | pkg. 26,2

kg | pal. 1104

☒ Floating laying

☒ Glued laying

☒ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives

