BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype MAPLE european

Description 3 layers of the same hardwood. The Maple has a very gentle whitish to yellowish

colour. The sorting Trend-Epoca is knotty, with a lively structure.

Brinell hardness 3,2 kp Gross density 0,63 g | cm³

2-Strip Country House Flooring MAPLE european "Trend-Epoca"



SURFACES

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



www.bergland-parkett.at

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy black heart	allowed
Cracks	allowed (partly filled)
Curled Spots differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Maple bar	alongside and crosswise partly allowed

-		 	
Tec	hn		ata
15.			

Length

Thickness 15 mm Useful layer approx. 5 mm

8 layers 2400 mm

Width 140 mm

(8 layers | pkg)

Fixlength

Connection Tongue and groove

m² | pkg. 2,69 | m² | pal. 112,98

kg|pkg. 26,2 | kg|pal. 1104

✓ Floating laying

✓ Glued laying

✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

