BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype ALDER natural

Description 3 layers of the same hardwood. The special features from Alder without heartwood

receives a light brown, reddish colour with decent brown colour inclusions. The sorting Wohngefühl is knotty, with a medium structure and the natural colour diffe-

rences.

Brinell hardness 1,7 kp Gross density 0,49 g | cm³

1-Strip Country House Flooring ALDER natural Wohngefühl "Alpbach"



SURFACES

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



www.bergland-parkett.at

Sorting guidelines					
Healthy knots	allowed (partly filled)				
Black knots	to approx. 35 mm allowed (partly filled)				
Healthy red heart	not allowed				
Healthy black heart	not allowed				
Cracks	slightly allowed (partly filled)				
Curled Spots differences in structure	slightly allowed				
Natural colour differences	allowed				
Natural fiber orientation	to one-third allowed				
Wormholes and insect-ate-spots	not allowed				
Sapwood	not allowed				
Red or brown spots	slightly allowed				
Stains from storage and light blueness	not allowed				
Knocked spots	not allowed				
Mirror	not allowed				

т 🗢	_ _		1	do	
	רוי	riic	ווי	α	ראו

Thickness 15 mm Useful layer approx. 5 mm

Width 150 mm

Length Lengthsystem 6 layers 1900 mm

(8 layers | pkg) 2 layers 950* mm

Connection Tongue and groove

One layer 950* mm consists of 2 boards

 $m^2 | pkg. 2,28$ | $m^2 | pal. 111,72$

kg|pkg. 23 | kg|pal. 1127

✓ Floating laying

✓ Glued laying

Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

