TYPES OF WOOD ALDER natural | steamed - ASH - BEECH natural | steamed - BIRCH BLACK WALNUT steamed - CHERRY natural | steamed - ELM steamed MAPLE -OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK - ZIRNOAK



Woodtype	ZIRNOAK european
Description	3 layers of the same hardwood. The european Zirnoak has a brown to medium brown colour tone. The sorting Ambiente is medium to very knotty, with a lively structure. The special feature are the naturally differences of colour.
Brinell hardness Gross density	4,2 kp 0,71 g cm³

1-Strip Country House Flooring ZIRNOAK european Ambiente "Palermo"



SURFACES

- Oil | wax oxidative dried
- Varnished 7-times
- ✓ Untreated sanded



www.bergland-parkett.at

Sorting guidelines			Technical data			
Healthy knots	allowed (partly filled)		Thickness	15 mm	Useful layer approx. 5 mm	
Black knots	allowed (partly filled)		Width	150 mm		
Healthy red heart	not allowed		Length	Lengthsystem	6 layers 1900 mm	
Healthy black heart	not allowed			(8 layers pkg)	2 layers 950* mm	
Cracks	allowed (partly filled)					
Curled Spots differences in structure	allowed		Connection Tongue and groove Due to the technical drying, the are no longer any pests, only the holes in the middle layer and bo			
Natural colour differences	allowed		One layer 950* mm consists of 2 boards layer**			
Natural fiber orientation	allowed		m² pkg.	2,28	m² pal. 111,72	
Wormholes and insect-ate-spots	not allowed are allowed in middle layer and back layer**					
Sapwood	allowed	kg pkg.		23	kg pal. 1127	
Red or brown spots	allowed		✓ Floating laying			
Stains from storage and light blueness	allowed		✓ Glued laying			
Knocked spots	allowed		Suitable for underfloor heating when gluing the entire area with solvent-free adhesives			
Mirror	alongside and crosswise allowed					

